



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: 2003013960 A

(43) Date of publication of application: 15.01.03

(51) Int. Cl.  
**F16C 33/32**  
**B23Q 1/40**  
**B23Q 11/12**  
**F16C 33/44**  
**F16C 33/62**  
**// B23B 19/02**

(21) Application number: 2001195069

(71) Applicant: NSK LTD

(22) Date of filing: 27.06.01

(72) Inventor:  
 NAWAMOTO HIROTSUNA  
 SAITO TAKESHI  
 KONNO MASARU  
 ARAMAKI HIROTOSHI

(54) HIGH SPEED ROLLING BEARING

COPYRIGHT: (C)2003,JPO

(57) Abstract:

**PROBLEM TO BE SOLVED:** To actualize low torque and low heat generation and improve a seizure-resistant property and wear-resistant property at high speed rotation.

**SOLUTION:** In an angular contact ball bearing used for high speed rotation in which a plurality of balls are arranged between an inner ring 11 and outer ring 12 via a retainer 14 and at least one of surfaces of their base material among an inner ring raceway, an outer ring raceway, balls 13, and a retainer 14 is formed by steel and a DLC film is also formed on the surface of the base material, the DLC film is provided with an intermediate layer made of metal components, a compound layer made of a carbon component, and a carbon layer. The compound layer is a graded layer in which composition is consecutively changed from the intermediate layer to the carbon layer, and plastic deformation hardness of the DLC film is set at 8 to 35 GPa.

